

BUILDING TRUST

PRODUCT DATA SHEET

SikaTop®-109 Seal IN

High performance flexible acrylic cementitious waterproofing coating (Formerly SikaTop® Seal-109 hi)

DESCRIPTION

SikaTop®-109 Seal IN is an elastomeric, liquid applied, crack bridging, two part high performance acrylic polymer modified cementitious waterproofing coating system with high degree of flexibility. It comprises of a liquid polymer and a cement based mix incorporating special admixtures. It is applied to concrete and mortar to prevent water infiltration, particularly in demanding applications and difficult environments.

USES

- Waterproofing applications for various structures such as:
 - Raw water concrete tanks, reservoirs, waste water tanks
 - Terraces, balconies, sunshades, etc.
 - Flat and small roofs
 - Basement and Retaining walls
 - Swimming pools, fountains, water bodies, canals
 - RCC gutters, drains and planter boxes
 - Wet areas like toilets, kitchen, utility, sunk slabs
 - Lift pits, sump, etc.

- Interior and exterior waterproofing and damp-proofing of concrete, cementitious rendering, brickwork and blockwork
- Protection of concrete structures against the effects of de-icing salts and freeze-thaw attack
- Pore / blowhole filling
- Sealing fine static cracks in concrete structures not subject to movement
- Sealing internal basement walls against dampness

CHARACTERISTICS / ADVANTAGES

- Easy to apply by brush, spray or flat trowel
- No additional water is required to make the slurry
- Pre-batched components with consistent quality
- Easy and fast mixing
- Highly water resistant, reduces saltpetre action and prevents carbonation
- Protects concrete from chloride penetration
- Non-corrosive to steel and iron
- Very flexible, good elongation
- Bonds well to all damp substrates
- Good abrasion resistance
- Good adhesion to reinforced concrete, mortar or masonry
- Fast curing

PRODUCT INFORMATION

Part A	Acrylic polymer	
Part B	Portland cement with selected ag- gregates and additives	
Part A+B pre-batched	50 kg set	
Part A	20 kg container	
Part B	30 kg bag	
12 months from date of production		
	Part B Part A+B pre-batched Part A Part B	

Product Data Sheet

SikaTop®-109 Seal INNovember 2023, Version 02.01
020701010020000224

Storage conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +10 °C and +35 °C. Liquid component must be protected from frost.				
Appearance / Colour	Part A+B mixed		Grey slurry		
, ippediance / coloui	Part A		White liquid		
	Part B		Grey powder		
TECHNICAL INFORMATION					
Tensile strength	~2 N/mm²		(AS	(ASTM D412)	
Elongation at break	~180 %		(AS	(ASTM D412)	
Tensile adhesion strength	~2 N/mm² (dry substrate)			(EN 1542)	
Water penetration under pressure	~0 mm penetratio	~0 mm penetration at 5 bar for 72 h (BS EN 12390-8			
Behaviour after artificial weathering	No chalking or cracking on the film when tested for 500 hours (IS 101				
SYSTEM INFORMATION					
System structure	Layer		Product		
	Base coat		SikaTop®-109 Seal IN		
	Top coat SikaTop®-109 Seal IN		op®-109 Seal IN		
	IMPORTANT				
	For larger application areas and high demanding applications, use a glass				
	fabric reinforcement Sika® Fabric-50 between the coats			al expos-	
APPLICATION INFORMATIO		[®] Fabric-50 is optional.			
APPLICATION INFORMATIO	IN				
Mixing ratio	Part A : Part B = 1	: 1.5 (by weight)			
Mixing ratio Fresh mortar density	Part A : Part B = 1 ~1.65 kg/L (Part A		(EN IS	O 2811-1)	
Fresh mortar density			(EN IS	0 2811-1)	
	~1.65 kg/L (Part A- Layer Base coat	+B mixed, +27 °C) Product SikaTop®-109 Sea	Consumption ~1 kg/m²	O 2811-1)	
Fresh mortar density	~1.65 kg/L (Part A-Layer Base coat Top coat	+B mixed, +27 °C) Product SikaTop®-109 Sea SikaTop®-109 Sea	Consumption ~1 kg/m² ~1.2 kg/m²		
Fresh mortar density	~1.65 kg/L (Part A-Layer Base coat Top coat Note: The consum	Product SikaTop®-109 Sea SikaTop®-109 Sea sption will vary depending ughness, surface profile,	Consumption ~1 kg/m² I IN ~1.2 kg/m² g on application area, so	ıbstrate	

Fresh mortar density	$^{\sim}$ 1.65 kg/L (Part A+B mixed, +27 °C)		(EN ISO 2811-1)		
Consumption	Layer	Product	Consumption		
	Base coat	SikaTop®-109 Seal IN	~1 kg/m²		
	Top coat	SikaTop®-109 Seal IN	~1.2 kg/m²		
	Note: The consumption will vary depending on application area, substrate type, substrate roughness, surface profile, absorption of the surface and thickness required.				
Layer thickness	~1 mm in 2 coats				
Ambient air temperature	+10 °C min. / +40 °C max.				
Substrate temperature	+10 °C min. / +40 °C max.				
Pot life	~40 minutes (100 g mass, +27 °C)				
Waiting time / Overcoating	Base layer	Overcoating layer	Waiting time		
	SikaTop®-109 Seal IN	SikaTop®-109 Seal IN	~4 h		
	SikaTop®-109 Seal IN	Screed / Plaster	~3 d		
	proximate and will be a	Note: Above values are at $+30$ °C and 50 % relative humidity. Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.			

BASIS OF PRODUCT DATA

vary due to circumstances beyond our control.

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may



FURTHER DOCUMENTS

Sika Method Statement: SikaTop®-109 Seal IN

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

EQUIPMENT

Mixing

Electric drill paddle mixer (> 700 W, 300 to 500 rpm)

Application

- Hard bristled brush
- Squeegee
- Flat trowel

SUBSTRATE QUALITY / PRE-TREATMENT

- The concrete substrate must be sound and with a minimum pull off strength of 1.0 N/mm².
- The substrate must be free of all traces of contaminants, loose and friable particles, cement laitance, oils and grease, wax, curing compounds, water repellent coatings etc.
- The substrate must be prepared by suitable mechanical preparation techniques such as high pressure water jetting, needle guns, grinding, blast cleaning etc.
- High spots must be removed by grinding.
- Weak concrete must be removed and surface defects such as blowholes and voids must be fully exposed.
- Repairs to the substrate, filling of blowholes/voids and surface levelling must be carried out using appropriate products from the Sikafloor®, Sikadur® and Sikagard® range of materials.
- All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.
- Any wax based curing compounds or water repellent coatings must be fully removed by scraping or grinding.
- All intersections of horizontal and vertical surfaces should be profiled with a mortar fillet of minimum 25 mm × 25 mm.

MIXING

IMPORTANT

Do not add water in any circumstances.

Waterproofing coating

- 1. Pour full quantity of SikaTop®-109 Seal IN Part A into a clean mixing container.
- While stirring slowly, add SikaTop®-109 Seal IN Part B.
- 3. Mix thoroughly for 3 minutes, until free from lumps and smooth consistency is achieved.

Waterproofing mortar

- Pour 90 % of SikaTop®-109 Seal IN Part A into a clean mixing container.
- 2. While stirring slowly, add SikaTop®-109 Seal IN Part R
- 3. Mix thoroughly for 3 minutes, until free from lumps and smooth consistency is achieved.

APPLICATION

IMPORTANT

SikaTop®-109 Seal IN may display signs of "blooming" after rain or in damp weather. This does not affect the performance of the coating in any way.

IMPORTANT

Do not apply in direct sun and/or strong wind. IMPORTANT

In areas of severe water penetration, three coats might be required.

IMPORTANT

Protect freshly applied material from freezing conditions, rains etc.

Detailing

- 1. Seal all penetrations with a suitable Sika sealant like SikaSwell® S-2 or Sikagard® 694 F(I) epoxy putty to prevent any leakage from the periphery of the down take pipes.
- Additionally, if so desired cut Sika® Fabric-50 to desired dimensions for detailing on intersections and also around pipe penetration by embedding it with the SikaTop®-109 Seal IN.
- 3. Sika® SealTape F is recommended to be used as a component of a composite sealing system in conjunction with SikaCeram® tile adhesive and ceramic tiles to achieve water tightness in wet rooms and around wet areas.

Waterproofing coating

- 1. Thoroughly pre-wet the prepared substrate (2 hours recommended) before application. Keep the surface wet and do not allow to dry. Before application remove excess water, e.g. with a clean sponge. The surface must appear a dark matt appearance without shining and surface pores and cavities must not contain water.
- 2. Apply the first coat of SikaTop®-109 Seal IN with a hard bristled brush or broom applied in the same direction and leave to harden for 2 to 6 hours.
- 3. (Optional) Wherever coating is to be reinforced with glass fabric, lay Sika® Fabric-50 into the freshly applied base coat and embed firmly into the wet coat with brush.
- Apply the second coat of SikaTop®-109 Seal IN in crosswise direction to the first application as soon as first coat has hardened.

Waterproofing mortar

 Thoroughly pre-wet the prepared substrate (2 hours recommended) before application. Keep the surface wet and do not allow to dry. Before application remove excess water, e.g. with a clean sponge. The surface must appear a dark matt appearance without shining and surface pores and cavities must not contain water.



SikaTop®-109 Seal INNovember 2023, Version 02.01
020701010020000224



- 2. Apply the first coat of SikaTop®-109 Seal IN by a flat trowel applied in the same direction and leave to harden for 2 to 6 hours. For pore / blowhole filling, tightly trowel into the pores / blowholes of the surface.
- 3. (Optional) Wherever coating is to be reinforced with glass fabric, lay Sika® Fabric-50 into the freshly applied base coat and embed firmly into the wet coat with trowel.
- Apply the second coat of SikaTop®-109 Seal IN in crosswise direction to the first application as soon as first coat has hardened.

Note:

If the second coat is applied 12 hours or later to first coat, the first coat shall be slightly pre-wetted by using a fine spray.

IMPORTANT

Slight fabric marks may be visible after application of the second coat, but it will have no adverse bearing on the performance of the waterproofing system.

Protection

- 1. The top coat while wet, sprinkle clean quartz sand.
- 2. Once top coat has sufficiently cured, apply protection plaster, mortar, screed or any other adhesive layer. A bonding agent may be necessary.
- 3. Alternatively, a separation layer like PE sheet or geotextile can be used before any plaster / screed / interlocking paver blocks.

CURING TREATMENT

Cure SikaTop®-109 Seal IN for minimum 7 days to ensure full cement hydration and minimise cracks. Use wet hessian cloth, spray curing or similar approved methods during the recommended period of curing.

CLEANING OF TOOLS

Clean all tools and application equipment with water immediately after use. Hardened material can only be removed mechanically.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

Sika India Pvt. Ltd.

620, Diamond Harbour Road Commercial Complex II Kolkata - 700 034 West Bengal, India

Contact:

Phone: +91 33 2447 2448 Fax: +91 33 2397 8688 info.india@in.sika.com www.sika.in









Product Data Sheet
SikaTop®-109 Seal IN
November 2023, Version 02.01
020701010020000224



LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaTop-109SealIN-en-IN-(11-2023)-2-1.pdf